

KKALPANA INDUSTRIES (INDIA) LIMITED

An ISO 9001:2008 company

TECHNICAL DATA

Silane Grafted XLPE Compound : KI – XL – 03HS & KI – XL – 04FX

DESCRIPTION :

A Low Density Cross Linkable Polyethylene Compound where silane is incorporated to PE through grafting; This product is suitable for Low Voltage Power Cables (LT applications).

The above product consists of 2 Components i.e. Grafted Polymer – Grade KI-XL-03HS & Catalyst Master Batch Grade KI-XL-04FX to be premixed prior to use at a ratio of 95:05.

Such system allows the compound to be extruded as a normal thermoplastic in a conventional PE (or even PVC) extrusion line, thus obviating the need of an expensive continuous vulcanizing (CV) extrusion line. The cross-linking step is subsequently carried out by immersion in hot water (Sauna), or exposure to steam. In each case, time of curing is to be optimized as a function of thickness of insulation, concentration of catalyst and temperature.

SPECIFICATIONS :

KI-XL-03HS & XL-04FX meets requirements as applicable under following standards, when processed using sound extrusion practice and testing procedure;

- IS 10810
- BS 5467, 5468, 6724, 7655
- IEC 60502

TYPICAL PROPERTIES:

A) XL-03HS

Property	Unit	Typical Value	Test Method
Density	gm / cm ³	0.923 – 0.925	ASTM-D-792
Melt Flow Index (190°C, 2.16 Kg)	gms / 10 Min	0.6 – 2.0	IS-10810 (Part-23) / ASTM-D-1238
Contamination (Visual)	No./Kg	< 5	KIL

MKT: TDS – 03HS/04FX – 10/15

B) XL-03HS / XL-04FX Combination

Mixed at 130°C at 95:5 ratio for 3 minutes. Compression moulded to a sheet of 1.5 mm thickness. Cured by immersion in water at 95°C for 3 hours. Conditioning for 3 hours.

Property	Unit	Typical Value	Test Method
Tensile Strength	MPa	16 - 19	IS-10810 (Part-7) / ASTM-D-638
Elongation at break	%	500 – 600	IS-10810 (Part-7) / ASTM-D-638
Hot set at 200 °C			
a) Hot Elongation after 15 min.	%	60 – 90	IS-10810 Part-30 / IEC 60811-1-2
b) Permanent Set after after 5 min	%	± 5	-- do --
Oven ageing at 135 °C, 168 hours			
a) Variation in Tensile Strength	%	± 15	IS-10810 Part-11 / IEC 60811-2-1
b) Variation in Elongation at Break	%	± 15	IS-10810 Part-11 / IEC 60811-2-1
Volume Resistivity	Ohm-cm	1 X 10 ¹⁶	IS-1991 / IEC 60093
Dissipation factor @ 1kHz, 25°C	-	0.0004	ASTM-D-150
Dielectric Constant @ 1kHz, 25°C	-	2.7 – 2.8	ASTM-D-150

PROCESSING GUIDELINES :

It is recommended to dry the Catalyst Master batch and colour Master batch (if any) at 60°C in air oven in 4-6 cm layers for 8-12 hours. The Grafted Polymer should never be pre-heated.

The Grafted Polymer and Catalyst Master batch should be manually mixed at a ratio 95:5 at room temperature without shearing, just before consumption. Mixing in large quantities should be avoided, since such leftover premix cannot be stored.

It is important that extruder should not be kept idle for more that 10 minutes when filled with XL-03HS / XL-04FX premix. It should be kept running at a low RPM if it is needed for changeover of size etc.

MKT: TDS – 03HS/04FX– 10/15

PACKAGING :

- Aluminum Foil Multilayer Bags of 25 kgs.
- 20' FCL will take palletized 11 MT. & 40' FCL will take 24.75 MT. Each pallet covered with PE Liner.

STORAGE :

The shelf life of the product is 90 days (In case of Export packaging the shelf life is guaranteed for 180 days instead of 90 days) from the date of production, subject to following conditions:

- Storage temperature not generally exceeding 25°C.
- Away from direct sunlight and weathering.
- Closed and unbroken bags.
- Use of compound within 3-4 hours after bags are open.

The information given in the document is believed to be reliable and is given in the good faith but without warranty. The user should test the product to ascertain the suitability for the intended use. Product specification or the whole document is subject to change without any prior notice.

MKT: TDS – 03HS/04FX – 10/15